



Devlon V-API

Physical Property	ASTM Test Method	Units	Value
Tensile strength 23°C	D638	MPa	79.92
		psi	11592
Tensile strength -40°C	D638	MPa	109.52
		psi	15885
Elongation at 23°C	D638	%	5.37
Elongation at break	D638	%	~
Hardness	D785	Shore D	78/80
		Rockwell R	112
Flexural strength	D790	MPa	121.55
		psi	17630
Deformation under load 140Kgf/cm ² at 23°C for 24 hours	D621	%	1.0/2.0
Charpy impact strength at 23°C	D256	J/M	54.8
		ftlbs/inch	12.3
Charpy impact strength at -40°C	D256	J/M	19.8
		ftlbs/inch	4.5
Modulus of elasticity	D638	MPa	4138
		psi	600175
Compressive strength	D695	MPa	140
		psi	20305
Compressive yield strength	D695	MPa	91.2
		psi	13227
Linear thermal expansion coefficient 30-100°C	E831	mm/mm/°C	1.11 x 10 ⁻⁴
Melt point	D3418	°C	216
Heat distortion temperature °C	D648	264 psi	93
		66 psi	209
Service temperature (short term)	D570	°C	190
Service temperature (long term)	D570	°C	125
Dielectric strength	D149	Kv/mm	>15
Specific gravity	D792	g/cm ³	1.14
Water absorption 24 hrs	D570	%	0.105
Water absorption saturation	D570	%	3
Flammability	UL 94	Burn rate	V2

1. The test figures stated are typical values and their aim is to assist the specifier in material selection. They are not intended to represent exact specifications.
2. ~denotes no data available at the time of publication. Please contact Devol for further information.
3. The information in this bulletin is to our best knowledge true and accurate but all instructions, recommendations or suggestions are made without guarantee. Since the conditions of use are beyond their control, Devol Engineering and its subsidiaries disclaim any liability for loss or damage suffered from use of these data or suggestions. Furthermore no liability is accepted if use of any product in accordance with these data or suggestions infringes any patent.